

Resfoam 1 KM

Ultra fluid, one-component polyurethane injection resin with adjustable reaction times, for waterproofing structures, grounds and rocks subject to intense water seepage



WHERE TO USE

- Waterproofing concrete structures and cracked masonry subject to water seepage, also under pressure.
- Waterproofing rocks subject to water seepage.
- Waterproofing permeable grounds saturated with water.

Some application examples

- Waterproofing tunnels subject to water seepage through cracks or cold joints between ashlars.
- Waterproofing wells or hydraulic structures that leak water through working joints or cracks.
- Repairing cracks in dams, canals and crest gates, even under the water bed.
- Sealing cracks in floorings or damp foundations saturated with water.

TECHNICAL CHARACTERISTICS

Resfoam 1 KM is a one-component polyurethane resin, free of halogens, made up of a mix of isocyanides, special additives and an accelerator prepared according to a formula developed in the Mapei research laboratories.

Before using, **Resfoam 1 KM** must be mixed with **Resfoam 1 KM AKS** (accelerator) that, in direct

relation to the used dosage (from 5 to 20% by weight of resin), has different reaction times, according to the needs on the job site.

After mixing with the accelerator and in the absence of damp conditions, **Resfoam 1 KM** has a pot life of approximately one hour.

During its pot life, **Resfoam 1 KM** must be injected through special packers into the structure that needs to be waterproofed, by a piston pump or a membrane for one-component products. When the resin is in contact with water, it forms a semi-rigid waterproof polyurethane foam.

Thanks to its high fluidity, **Resfoam 1 KM** penetrates into several hundred micron wide cracks and can seal them even if they are subject to water seepage.

Once set, after 40-80 seconds depending on the temperature and the amount of added accelerator, **Resfoam 1 KM** ensures complete waterproofing of the treated area.

RECOMMENDATIONS

To consolidate cracked concrete structures that, at the moment of injection, are not subject to water seepage or strong dampness, use **Epojet**, fluid epoxy resin.

In the case of water seepage under strong pressure, it is necessary to increase the amount of **Resfoam 1 KM AKS** accelerator up to 20% of the

resin and in any case try to reduce the water pressure, even momentarily, when injecting the product.

If the injection treatment must carry out a structural consolidation function, it is preferable to use **Foamjet F** or **Foamjet T**, two-component polyurethane resins for the consolidation of cracked concrete and rocks subject to water seepage, that, through reaction, become a very strong foam.

APPLICATION PROCEDURE

Sealing cracks by injection

Place the injectors. Site off-set holes on the sides of the cracks. The size of the holes should fit the diameter of the injectors that will be used. Expansion injectors with a non-return valve, can be easily fixed, by their rotation, to block them completely to the walls of the hole. If there is no water seepage, normal metal or plastic pipes with a diameter of approximately 10 mm can be used and can be fixed with **Adesilex PG1**. However, it is necessary to inject water before injecting **Resfoam 1 KM** in order to obtain an expanding reaction.

In the presence of water seepages, standard metallic or plastic pipes with a diameter of approximately 10 mm can be used and must be fixed with **Lamposilex**.

Preparing and injecting the product

Resfoam 1 KM is mixed directly in its drum with approximately 10% **Resfoam 1 KM AKS** accelerator (20% if a very quick reaction is needed). After mixing, in the absence of damp or water, it can be injected for approximately 1 hour (it is necessary to protect the product from contact with damp air by covering the drum with its lid).

Note: *if, after mixing with the accelerator, Resfoam 1 KM is not protected from damp, a thin film can form over the surface (within 30 minutes from its preparation). However this does not interfere with the use of the material.*

Inject **Resfoam 1 KM** continuously into the crack. **Resfoam 1 KM** increases its volume as soon as it is in contact with water (after approximately 8-20 seconds in line with the temperature and damp) sealing cracks and blocking water seepages.

In the absence of water **Resfoam 1 KM** does not expand and continues to penetrate into the cracks.

Consolidating the ground and rock

The product must be prepared in the same way as for injecting cracks in concrete structures. While injecting and when **Resfoam 1 KM** is in contact with water, it increases in volume. This causes a slight

pressure on the single grains of the ground, tamping them. As a consequence of this, a polyurethane waterproof layer is formed, which varies in thickness, and permanently consolidates the injected material.

Cleaning

The tools used for injection (pump and pipes) must be washed with mineral oil or special solvents free from water and impurities.

CONSUMPTION

In open air, 1 kg of **Resfoam 1 KM** + 0.1 kg of **Resfoam 1 KM AKS** produces 50 litres of expanded foam on contact with 0.1 litres of water.

PACKAGING

Resfoam 1 KM (resin): 10 kg metal drums.

Resfoam 1 KM AKS (accelerator): 1 kg plastic drums.

STORAGE

Store the product in a dry sheltered place in its original sealed packaging at a temperature between +10°C and +30°C.

SAFETY INSTRUCTIONS FOR THE PREPARATION AND APPLICATION

Resfoam 1 KM contains diphenyl-methane di-isocyanides which is harmful and causes sensitivity when inhaled. It is irritant to eyes, respiratory system and skin.

It is recommended to protect eyes with goggles, and skin with gloves while preparing and using the product. Use the product only in well ventilated areas and protect respiratory apparatus. In case of contact with eyes and skin, wash with plenty of clean water and consult a doctor.

FOR PROFESSIONALS.

WARNING

N.B. - Although the technical details and recommendations contained in this product report correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

**All relevant references
of the product are available
upon request**

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

	Resfoam 1 KM (resin)	Resfoam 1 KM AKS
Specific gravity (g/cm³):	1.18 at +20°C	1.21
Colour:	dark brown/redish	redish
Viscosity (at +5°C) (mPa·s):	700 ± 50	25 ± 5
Viscosity (at +10°C) (mPa·s):	430 ± 5	25 ± 5
Viscosity (at +15°C) (mPa·s):	380 ± 50	25 ± 5
Viscosity (at +23°C) (mPa·s):	200 ± 30	25 ± 5
Hazard classification according to EC 99/45:	harmful. It is recommended to carefully read the instructions for use and refer to the safety data sheet	
Storage:	6 months in original sealed packaging, protect from moisture and store at a temperature between +10°C and +30°C	
Customs class:	3909 50 90	

APPLICATION DATA

Reaction in relation to the temperature with 10% accelerator:				
– temperature:	5°C	10°C	15°C	23°C
– initial growth time in seconds:	21	19	17	11
– end growth time in seconds:	80	76	68	62
Reaction in relation to the temperature with 15% accelerator:				
– temperature:	5°C	10°C	15°C	23°C
– initial growth time in seconds:	18	15	12	8
– end growth time in seconds:	62	50	48	41
Expansion ratio in free air:	40-60			
Dimensionally stable:	yes			

Resfoam 1 KM

(GB) A.G. BETA

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution



BUILDING THE FUTURE

MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)



CERTIQUALITY
No. 250/2



ISO 14001
Mediglia, Italy plant
CERTIQUALITY No.1280/1



EMAS
VERIFIED ENVIRONMENTAL MANAGEMENT
PLANT OF MEDIGLIA



OHSAS 18001
CERTIFIED BY CERTIQUALITY
MAPEI PLANT IN ROVERETO (TN)
Certificate No. 3586
MAPEI



CERTIQUALITY
No. 3358



ITC
No. 00 0083 SJ

MAPEI S.p.A. - ITALY


MAPEI FAR EAST Pte Ltd

MAPEI Sro - CZECH REP.



CERTIQUALITY
No. 1517/1

MAPEI FRANCE



DNV
No. 94-OSL-AQ-6236

RESCON MAPEI AS - NORWAY



EMAS
VERIFIED ENVIRONMENTAL MANAGEMENT
PLANT OF SAGSTUA

MAPEI KFT. - HUNGARY



DNV
No. 12026-2002
AQ-BUD-TGR

MAPEI INC - CANADA



QMI
No. 004157

MAPEI ARGENTINA S.A.



IRAM
No. AR-QS-688

www.mapei.com

2004-4-2003