


Idrostop

Hydrophilic expandable rubber section for watertight construction joints



WHERE TO USE

For creating water light construction joints in civil, industrial, and hydraulic construction.

Some application examples

- Waterproof joints between concrete beds and elevation walls.
- Waterproof contact joints between different building materials, e.g. steel and concrete, or stone and concrete.
- Contact joints between different types of materials, e.g. PVC or steel tubing going through poured concrete in swimming pools, sewage-treatment tanks, reservoirs, and hydraulic projects in general.
- Waterproof cooling joints (temporary shrinkage joints) created during pouring to reduce the risk of cracking in long or monolithic structures.
- Waterproof construction joints where conventional water-stop cannot be installed easily and securely because of the high density of the reinforcing.
- Waterproof construction joints in tunnels, dams and hydraulic projects including reservoirs for drinking water.

TECHNICAL CHARACTERISTICS

Idrostop is a pre-formed flexible strip, with an acrylic polymer base specially designed to form watertight

construction joints in construction up to a hydraulic pressure of 5 atm.

Idrostop is available in two sizes, 20x10 mm and 20x15 mm, labelled **Idrostop 10** and **Idrostop 15**.

Idrostop does not contain bentonite.

Because of its chemical composition **Idrostop** expands gradually in permanent contact with water, creating an active barrier against water pressure (positive and negative). Unlike other materials that tend to lose efficiency following repeated cycles of expansion and contraction, **Idrostop** maintains its properties unchanged even in the presence of aggressive water such as salt water (sea water), and water in sewage treatment plants and sewers.

Idrostop is stable at temperatures between -30°C and $+50^{\circ}\text{C}$.

RECOMMENDATIONS

- **Idrostop** cannot be installed if the structure is immersed in water at the time of application. Remove any free water from the surface and wait several hours before installing the strip.
- **Idrostop** cannot be used if the surface of the installation is heavily contaminated with acids or solvents. Clean the surface thoroughly and consult the Mapei Technical Assistance.

Idrostop

APPLICATION PROCEDURE

Substrate preparation

The surface of the concrete must be clean and solid when **Idrostop** is installed.

Remove any cement laitance with a brush and sweep away any deposits that may have been left during pouring. **Idrostop** can even be applied on slightly damp surfaces.

Installation

Idrostop strip can be applied on concrete, metal, PVC, and natural stone with **Idrostop Mastic**, a ready-to-use, solvent-free single component adhesive based on MS polymers.

Idrostop Mastic is available in 290 ml cartridges.

After extrusion the mastic becomes a thixotropic paste easily applied vertically and horizontally. It reticulates with moisture to form a flexible product at temperatures from +10°C to +40°C.

Make a hole in the cartridge above the threads and screw in the nozzle, cutting an opening with a diameter of 5 mm at a 45° angle. Insert the cartridge into a normal gun and extrude the adhesive onto the surface of an **Idrostop** section that has been cut to size beforehand, or directly onto the concrete.

Then press the **Idrostop** onto the substrate, moving it slowly in all directions to make it adhere thoroughly at all points without exerting traction.

Forming corners or seams does not require any special procedure. Simply align the pieces of **Idrostop** together and their subsequent expansion will ensure a perfect seal against water pressure.

To facilitate application on vertical surfaces, it is recommended that **Idrostop** be cut into pieces 1 meter long.


This precaution makes installation fast and secure because it eliminates any potential sliding caused by the weight of the strip.

Longer pieces can however be installed by mechanically attaching the top end of the **Idrostop** with screws or nails, extruding a line of adhesive directly onto the substrate.


Idrostop must then be pressed onto the fresh adhesive to make it adhere.

Idrostop can also be solely attached mechanically with screws or nails placed in a row along the strip, spaced not more than 25 cm apart, to ensure thorough contact with the substrate.


Concrete can be poured immediately after the **Idrostop** is installed if attached




Cut the Idrostop strip to the desired length




Apply Idrostop Mastic evenly on the Idrostop or directly to the substrate




Firm Idrostop, press it and move it in all directions to make it adhere well



Idrostop can be placed also with screws or nails. Place nails every 25 cm



In line joint. Butt jointing of two pieces of Idrostop



In line joint. The two ends are staggered with a 2-3 cm overlap for a better seal

TECHNICAL DATA (typical values)

PRODUCT IDENTITY


Form:	pre-formed strip
Colour:	blue
Available sizes:	20x10 mm (Idrostop 10) 20x15 mm (Idrostop 15)
Specific gravity:	1.30 g/cm ³ at +20°C
Solubility in water:	insoluble
Principle properties:	expands when in contact with water
Storage:	12 months in original sealed packaging stored in a dry place
Health hazard classification acc. to EEC 88/379:	none
Customs class:	3916 10 00
Corrosive:	non corrosive

APPLICATION DATA:


Application temperature range allowed using Idrostop Mastic as adhesive:	from +10°C to +40°C
Waiting time before pouring concrete if the installation has been carried out with Idrostop Mastic:	24 hours
Waiting time before pouring concrete if the installation has been carried out screws and nails:	no waiting time required
Consumption of Idrostop Mastic:	approximately 250 ml per 10 linear metres of Idrostop 10 and Idrostop 15

FINAL PERFORMANCES


Expansion in water:	
– after 24 hours:	approximately 45%
– after 2 days:	approximately 70%
– after 3 days:	approximately 82%
– after 7 days:	approximately 120%
Impermeability:	up to 5 atm
Maximum joint width:	7 mm
Elongation % according to ASTM 638 M-89:	70-100%
Shore hardness according to DIN 53505:	25-35



Horizontal corner joint




Vertical joint between floor and wall




For application on vertical surfaces it is recommended to install the gasket in length of about 1 m


Idrostop



Pieces longer than 1 m can be installed on vertical surfaces by fixing the top of the pieces with a nail or pin and then extruding the Idrostop Mastic directly onto the underlying substrate.



Thickness of concrete to protect Idrostop



Where two strips of Idrostop are used side by side, 6 cm of concrete is sufficient to protect the gasket

mechanically with screws and nails. If **Idrostop** has been attached with **Idrostop Mastic**, wait 24 hours before pouring the concrete.

The waiting time can be shortened, if necessary, but a minimum of 4 hours must pass after installing the **Idrostop Mastic**. In this case it is recommended that nails or screws be placed every 1 meter to prevent

the **Idrostop** from moving during the pour. The thickness of the protection pour of **Idrostop** should not be less than 8 cm.

Cleaning

Wet **Idrostop Mastic** can be removed from tools with common solvents (ethyl acetate, benzene, toluene). Once reticulation is complete, tools can only be cleaned mechanically.

PACKAGING

Idrostop is available in two sizes in cartons:

- **Idrostop 10** (20x10 mm); six 10 m rolls;
- **Idrostop 15** (20x15 mm); six 7 m rolls.

STORAGE

Store in a dry place at temperatures between +10°C and +40° C.

WARNING

N.B. - Although the technical details and recommendations contained in this product report correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

